



Flexterra® High Performance-Flexible Growth Medium™(HP-FGM™)

SDS Number: CON062

Revision Date: 1/1/17

Page 1 of 6

1 **PRODUCT AND COMPANY IDENTIFICATION****Manufacturer**

PROFILE Products, LLC
750 LAKE COOK ROAD
SUITE 440
BUFFALO GROVE, IL 60089

Emergency: Emergency Phone: (800) 424-9300 (ChemTrec)
Contact: ChemTrec Acct #: CCN792719
Phone: (847) 215-1144
Fax: (847) 215-0577
Email: tech@profileproducts.com
Web: www.profileproducts.com

Product Name: Flexterra® High Performance-Flexible Growth Medium™(HP-FGM™)
Revision Date: 1/1/17
SDS Number: CON062
CAS Number: Not applicable
Product Use: Erosion control and revegetation mulch for hydraulic seeding.

Product Description: Green dyed wood fibers, biodegradable fibers, minerals and a proprietary binder mixture.

2 **HAZARDS IDENTIFICATION****Classification of the Substance or Mixture****GHS Classification in Accordance with 29 CFR 1910 (OSHA HCS):**

No GHS Classifications Indicated

GHS Label Elements, Including Precautionary Statements**GHS Signal Word:** **NONE**

no GHS pictograms indicated for this product

GHS Hazard Statements:

no GHS hazards statements indicated

GHS Precautionary Statements:

no GHS precautionary statements indicated

Hazards not Otherwise Classified (HNOC) or not Covered by GHS

Route of Entry: Inhalation, skin contact, eye contact

Inhalation: Wood may cause sneezing, irritation, and dryness of the nose and throat. Dust may aggravate pre-existing respiratory conditions.

Skin Contact: Wood dust can cause irritation. Skin absorption is not known to occur.

Eye Contact: Wood dust can irritate the eyes.

Ingestion: No reports of human ingestion.

OSHA Classification: Wood dust is a hazardous substance as defined by the Hazard Communication Standard 29CFR 1910.1200


Flexterra® High Performance-Flexible Growth Medium™(HP-FGM™)

SDS Number: CON062

Revision Date: 1/1/17

Page 2 of 6

NFPA: Health = 1, Fire = 1, Reactivity = 0, Specific Hazard = n/a



3 COMPOSITION/INFORMATION OF INGREDIENTS

Ingredients:

Cas#	%	Chemical Name
0	Proprietary	Hydrocolloidal Based Polysaccharide Tackifier
9000300	Proprietary	Guar Gum

4 FIRST AID MEASURES

- Inhalation:** Usually not a problem. Remove to fresh air if respiratory irritation develops, and get medical aid promptly if irritation persists. In high dust levels wear dust mask.
- Skin Contact:** Usually not a problem. Wash off with running water if irritation is experienced.
- Eye Contact:** Open eyelids and flush with water.
- Ingestion:** Get medical attention.

5 FIRE FIGHTING MEASURES

- Flammability:** Combustible product
 - Flash Point:** Not applicable
 - Flash Point Method:** Not applicable
 - Autoignition Temp:** 200-260°C (400-500°F)
- Conditions to avoid: In contact with flames or hot surfaces.
 Flammable- Extinguish with water; same as a wood fire

6 ACCIDENTAL RELEASE MEASURES

Scoop up product. Wear goggles and respirator if dust is produced in unventilated areas. Wet product will be slippery.

7 HANDLING AND STORAGE

- Handling Precautions:** Clean up areas where dust settles. Minimize blowdown or other practices that generate high airborne dust concentrations.
- Storage Requirements:** Store in a cool, dry place. Keep away from sources of ignition.



Flexterra® High Performance-Flexible Growth Medium™(HP-FGM™)

SDS Number: CON062

Revision Date: 1/1/17

Page 3 of 6

8 EXPOSURE CONTROLS/PERSONAL PROTECTION

Engineering Controls: None required for outdoor mixing and application. Use dust collection system for indoor handling operations.

Personal Protective Equipment: Eye Protection: Wear goggles when emptying bags and during other operations where there is a risk of dust entering the eyes.
 Gloves: Leather, plastic or rubber gloves could be worn to minimize skin irritation.
 Respirators: When handling methods generate dust at concentrations that exceed occupational exposure limits, wear a NIOSH approved respirator. A fabric respirator or a facepiece respirator with dust cartridges will generally provide adequate protection.
 Footwear: The product is slippery when wet. Wear appropriate footwear.

9 PHYSICAL AND CHEMICAL PROPERTIES

Appearance: Dyed green wood fibers - Pine & mixed hardwoods

Physical State: Wood Fibers **Odor:** Mild wood odor

Spec Grav./Density: Lighter than water

Vapor Pressure: N/A

10 STABILITY AND REACTIVITY

Chemical Stability: Stable product.

Conditions to Avoid: Contact with strong acids and oxidizers may generate heat. Product may ignite at temperatures in excess of 200°C (400°F).

Materials to Avoid: Strong acids and oxidizers.

Hazardous Polymerization: Will not occur.

11 TOXICOLOGICAL INFORMATION

EFFECTS OF CHRONIC EXPOSURE:

Inhalation: Frequent and repeated exposure to wood dust is associated with an increased risk of developing nasal cancer.
 Skin Contact: Although rare, wood dust may cause dermatitis in sensitized people.

Occupational Exposure Limits:

Wood dusts- All other species: ACGIH (2007): TLV-TWA 1 mg/m³ (Inhalable fraction); A4

Particulates Not Otherwise Regulated (PNOR): OSHA: PEL-TWA 15 mg/m³ (Total Dust); 5 mg/m³ (Respirable fraction)

Irritancy: Wood dust is a mild irritant
 Sensitization: Some wood dusts may cause allergic skin reactions

**Flexterra® High Performance-Flexible Growth Medium™(HP-FGM™)**

SDS Number: CON062

Revision Date: 1/1/17

Page 4 of 6

12

ECOLOGICAL INFORMATION

Guar Gum (CAS# 9000-30-0) is listed as an inert ingredient permitted for use in nonfood use pesticide products by EPA. It is also classified under the Federal Insecticide, Fungicide and Rodenticide Act (FIFRA) as a minimal risk inert substance (List 4A) meaning that as a pesticide, Guar Gum is considered by the EPA to pose little or no risk to humans or the environment. The US Department of Agriculture (USDA) National Organic Program (NOP) also allows the use of Guar Gum in a variety of applications, but primarily as a pesticide in organic production operations. Finally, Guar Gum is listed on the Generally Recognized as Safe (GRAS) list by the Food and Drug Administration (FDA).

48-hr LC_{50} = >100% for *Daphnia magna* when runoff generated using ASTM D7101 (2"/hr rainfall rate) was tested according to EPA-821-R-02-012.

13

DISPOSAL CONSIDERATIONS

Normally can be disposed of as a wood residue. Ensure disposal is in compliance with local, provincial (state), and federal regulations.

14

TRANSPORT INFORMATION



Flexterra® High Performance-Flexible Growth Medium™(HP-FGM™)

SDS Number: CON062

Revision Date: 1/1/17

Page 5 of 6

15 REGULATORY INFORMATION

Component (CAS#) [%] - CODES

Hydrocolloidal Based Polysaccharide Tackifier (0) [Proprietary]

Guar Gum (9000300) [Proprietary] TSCA

Regulatory CODE Descriptions

TSCA = Toxic Substances Control Act

COMPONENT / (CAS/PERC) / CODES

*Guar gum (9000300 n/a%) TSCA

REGULATORY KEY DESCRIPTIONS

MASS = MA Massachusetts Hazardous Substances List

NRC = Nationally Recognized Carcinogens

OSHA = OSHA workplace Air Contaminants

PA = PA Right-To-Know List of Hazardous Substances

TXAIR = TX Air Contaminants with Health Effects Screening Level

CERCLA = Superfund clean up substance

CSWHS = Clean water Act Hazardous substances

EHS302 = Extremely Hazardous Substance

EPCRAWPC = EPCRA Water Priority Chemicals

HAP = Hazardous Air Pollutants

NJEHS = NJ Extraordinarily Hazardous Substances

NJHS = NJ Right-to-Know Hazardous Substances

OSHAPSM = OSHA Chemicals Requiring process safety management

SARA313 = SARA 313 Title III Toxic Chemicals



Flexterra® High Performance-Flexible Growth Medium™(HP-FGM™)

SDS Number: CON062

Revision Date: 1/1/17

Page 6 of 6

TSCA = Toxic Substances Control Act

16	OTHER INFORMATION
----	--------------------------

Disclaimer:

Although reasonable care has been taken in the preparation of this document, we extend no warranties and make no representations as to the accuracy or completeness of the information contained herein, and assume no responsibility regarding the suitability of this information for the user's intended purposes or for the consequences of its use. Each individual should make a determination as to the suitability of the information for their particular purpose(s).

Section 31 25 14.13 – Hydraulically-Applied Erosion Control: High Performance-Flexible Growth Medium™

GENERAL

1.01 SUMMARY

- A. This section specifies the hydraulically-applied erosion control product Flexterra® High Performance-Flexible Growth Medium™ (HP-FGM™). Flexterra HP-FGM is a biodegradable material, composed of 100% recycled, Thermally Refined™ virgin wood fibers, crimped biodegradable interlocking fibers derived from regenerated cellulose sourced from sustainably harvested wood, micro-pore granules, naturally derived cross-linked biopolymers and water absorbents. The HP-FGM is patented, made in the US, plastic-free, and phytosanitized to eliminate potential weed seeds and pathogens. Flexterra requires no curing period and upon application forms an intimate bond with the soil surface to create a continuous, porous, absorbent and flexible erosion resistant blanket that allows for rapid germination and accelerated plant growth.
- B. Related Sections: Other Specification Sections, which directly relate to the work of this Section include, but are not limited to the following:
1. *Section 01 57 00 – Temporary Erosion and Sediment Control*
 2. *Section 02 24 23 – Chemical Sampling and Analysis of Soils*
 3. *Section 31 00 00 – Earthwork*
 4. *Section 31 91 00 – Planting Preparation*
 5. *Section 32 01 90.16 – Amending Soils*
 6. *Section 32 92 00 – Turf and Grasses*

1.02 SUBMITTALS

- A. Product Data: Submit manufacturer's product data and installation instructions. Include required substrate preparation, list of materials and application rate.
- B. Certifications: Manufacturer shall submit a letter of certification that the product meets or exceeds all technical and packaging requirements and is made in the U.S.A.

1.03 DELIVERY, STORAGE AND HANDLING

- A. Deliver materials and products in UV and weather-resistant factory labeled packages. Store and handle in strict compliance with manufacturer's instructions and recommendations. Protect from damage, weather, excessive temperatures and construction operations.

PRODUCTS

2.01 ACCEPTABLE MANUFACTURER

- A. PROFILE Products LLC
750 Lake Cook Road – Suite 440
Buffalo Grove, IL 60089
International - +1-847-215-1144
United States and Canada – 800-366-1180 (Fax 847-215-0577)
www.profileproducts.com

2.02 MATERIALS

- A. The HP-FGM shall be Flexterra HP-FGM and conform to the following typical property values when uniformly applied at a rate of 3,500 pounds per acre (3,900 kilograms/hectare) under laboratory conditions.

Property	Test Method	Tested Value (English)	Tested Value (SI)
Physical			
Mass/Unit Area	ASTM D6566	≥11.6 oz/yd ²	≥390 g/m ²
Thickness	ASTM D6525 ¹	≥ 0.22 inch	≥ 5.6 mm
Ground Cover	ASTM D6567 ¹	≥ 99%	≥ 99%
Water Holding Capacity	ASTM D7367	≥ 1,700%	≥ 1,700%
Material Color	Observed	Green	Green
Performance			
Cover Factor ²	ASTM D8298-Type 1	≤ 0.01	≤ 0.01
% Effectiveness ³	ASTM D8298-Type 1	≥ 99%	≥ 99%
Vegetation Establishment	ASTM D7322	≥ 800%	≥ 800%
Functional Longevity ⁴	ASTM D5338	≤ 18 months	≤ 18 months
Cure Time	Observed	0 - 2 hours	0 - 2 hours
Environmental Properties			
Ecotoxicity ⁵	EPA 2021.0	Non-Toxic	Non-Toxic
Biodegradability	ASTM D5338	Yes	Yes
Certified BioPreferred® Biobased Content	ASTM D6866	100%	100%
Elemental Impurity Limits	ASTM D8082	Pass	Pass

1. ASTM test methods developed for Rolled Erosion Control Products and have been modified to accommodate Hydraulically-Applied Erosion Control Products.
2. Cover Factor is calculated as soil loss ratio of treated surface versus an untreated control surface.
3. % Effectiveness = One minus Cover Factor multiplied by 100%.
4. Functional Longevity is the estimated time period, based upon field observations, that a material can be anticipated to provide erosion control and agronomic benefits as influenced by composition, as well as site-specific conditions, including; but not limited to – temperature, moisture, light conditions, soils, biological activity, vegetative establishment and other environmental factors.
5. 48-hour LC₅₀ > 100% - LC₅₀ refers to the percent concentration of a substance in water when 50% percent mortality of an organism is reached. 50% mortality of the tested species (*Daphnia magna*) could not be achieved when subjected to 100% effluent concentration proving the material to be acutely non-toxic.

2.03 COMPOSITION

- A. All components of the HP-FGM shall be pre-packaged by the Manufacturer to assure both material performance and compliance with the following values. Under no circumstances shall field mixing of components be permitted. No chemical additives with the exception of fertilizer, soil neutralizers and biostimulant materials should be added to this product.
1. Thermally Processed* (within a pressurized vessel) Virgin Wood Fibers – 80%
*Heated to a temperature greater than 380 degrees Fahrenheit (193 degrees Celsius) for 5 minutes at a pressure greater than 50 psi (345 kPa)
 2. Wetting agents (including high-viscosity colloidal polysaccharides, cross-linked biopolymers, and water absorbents) – 10%
 3. Crimped, Biodegradable Interlocking Fibers derived from regenerated cellulose sourced from sustainably harvested wood – 5%
 4. Micro-Pore Granules – 5%

2.04 PACKAGING

- A. Bags: Net Weight – 50 lb (22.7 kg), UV and weather-resistant plastic film
Pallets: Weather-proof, stretch-wrapped with UV resistant pallet cover
Pallet Quantity: 40 bags/pallet or 1 ton (909 kg)/pallet

EXECUTION

3.01 SOIL TESTING

- A. Soil Samples shall be taken and sent to a third-party, independent lab for analysis and in compliance with Section 02 24 23 – Chemical Sampling and Analysis of Soils, if applicable.
- B. The tests shall include analysis and interpretation of results.
- C. The soil testing methods used shall be compliant with recognized agronomic testing standards, as outlined in Section 02 24 23, for revegetation of disturbed sites.
- D. Soil Analysis shall include results for:
 - 1. Soil pH
 - 2. Soluble Salts
 - 3. Excess Carbonate
 - 4. Organic Matter
 - 5. Nutrient readings for:
 - i. Nitrogen, Phosphorus, Potassium
 - ii. Magnesium, Calcium, Sodium, Manganese, Sulfur, Zinc, Copper, Iron, Boron
 - 6. Cation Exchange Capacity
 - 7. Percent Base Saturation Sodium
- E. ProGanics® BSM, BioPrime™, JumpStart™, Aqua-pHix™ and NeutralLime™ Dry or other amendments shall be specified according to Section 32 01 90.16 – Amending Soils and applied with the hydroseeding slurry at Manufacturer recommended rates based on soil test results.

3.02 VEGETATION SPECIES SELECTION

Once soils have been analyzed for agronomic potential and amendment recommendations, selection of suitable plant species for achieving sustainable growth and effective erosion control is vital. Seed selection can be performed by a qualified seed supplier, consulting professional and/or regulatory agency. In lieu of this, a warm, extreme warm, or cool season Vegetator® variety mix may be considered. Species selection and establishment shall be compliant with Section 32 92 00 – Turf and Grasses, if applicable.

- A. Site and project specific information considered for species selection shall include:
 - 1. Project Location and Planning
 - i. Climate
 - ii. Elevation
 - iii. Aspect
 - iv. Slope/Gradient
 - v. Permanent or Temporary Planting
 - vi. Installation Date(s)
 - 2. Soil Conditions
 - i. Soil Texture
 - ii. Soil pH
 - iii. Toxicities/Deficiencies noted in the previous section.
 - 3. Site Maintenance Requirements
 - i. Mowing
 - ii. Irrigation
 - iii. Animal grazing preference
 - 4. Preferred Vegetation
 - i. Drought Tolerant
 - ii. Native Vegetation

- iii. Shrub Species
- iv. Turf Grasses
- v. Cool Season
- vi. Warm Season
- vii. Blend of Cool and Warm Season
- viii. Legume Species
- ix. Cover Crops

3.03 SUBSTRATE AND SEEDBED PREPARATION

- A. Examine substrates and conditions where materials will be applied. Apply products to geotechnically stable slopes that have been designed and constructed to divert runoff away from the face of the slope. Do not proceed with installation until satisfactory conditions are established.
- B. Depending upon project sequencing and intended application, prepare seedbed in compliance with other specifications under Section 1.01 B

3.04 INSTALLATION

- A. Strictly comply with equipment manufacturer's installation instructions and recommendations. Use approved hydroseeding machines with fan-type nozzle (50-degree tip). To achieve optimum soil surface coverage, apply HP-FGM from opposing directions to soil surface. Rough surfaces (rocky terrain, cat tracked and ripped soils) may require higher application rates to achieve 100% cover. Slope interruption devices or water diversion techniques are recommended when slope lengths (3H:1V) exceed 100 feet (30 m). Slope interruption intervals may need to be decreased based on steeper slopes or other site conditions. HP-FGM is not recommended for channels or areas with concentrated water flow unless used in conjunction with a rolled erosion control product designed to accommodate the anticipated hydraulic conditions. Unless approved by the Manufacturer, no chemical additives with the exception of fertilizer, soil neutralizers and biostimulant materials should be added to this product.
- B. For Erosion Control and Revegetation: To ensure proper application rates, measure and stake area. For maximum performance, apply HP-FGM in a two-step process*:
 - 1. *Step One: Apply fertilizer with specified prescriptive agronomic formulations and typically 50% of specified seed mix with a small amount of HP-FGM for visual metering. Do not leave seeded surfaces unprotected, especially if precipitation is imminent.*
 - 2. *Step Two: Mix balance of seed and apply HP-FGM at a rate of 50 lb per 125 gallons (22.7 kg/475 liters) of water over freshly seeded surfaces. Confirm loading rates with equipment manufacturer.*

**Depending upon site conditions HP-FGM may be applied in a one-step process where all components may be mixed together in single tank loads. Consult with Manufacturer for further details.*

Best results and more rapid curing are achieved at temperatures exceeding 60°F (15°C). Curing times may be accelerated in high temperature, low humidity conditions with product applied on dry soils.

- C. Mixing: A mechanically agitated hydroseeding machine is strongly recommended:
 - 1. *Fill 1/3 of mechanically agitated hydroseeder with water. Turn pump on for 15 seconds and purge and pre-wet lines. Turn pump off.*
 - 2. *Turn agitator on and load low density materials first (i.e. seed).*
 - 3. *Continue slowly filling tank with water while loading fiber matrix into tank.*
 - 4. *Consult application and loading charts to determine number of bags to be added for desired area and application rate. Mix at a rate of 50 lb of HP-FGM per 125 gallons (22.7 kg/475 liters).*
 - 5. *All HP-FGM should be completely loaded before water level reaches 75% of the top of tank.*
 - 6. *Top off with water and mix until all fiber is fully broken apart and hydrated (minimum of 10 minutes — increase mixing time when applying in cold conditions). This is very important to fully activate the bonding additives and to obtain proper viscosity.*
 - 7. *Add fertilizer and any other remaining amendments.*
 - 8. *Shut off recirculation valve to minimize potential for air entrainment within the slurry.*
 - 9. *Slow down agitator and start applying with a 50-degree fan tip nozzle.*

10. *Spray in opposing directions for maximum soil coverage.*

- D. Application Rates: These application rates are for standard conditions. Application rates may need to be increased to accommodate very rough surfaces.

Slope Gradient / Condition	English	SI
< 4H to 1V	2,500 lb/ac	2,800 kg/ha
> 4H to 1V and < 3H to 1V	3,000 lb/ac	3,400 kg/ha
> 3H to 1V and < 2H to 1V	3,500 lb/ac	3,900 kg/h
> 2H to 1V and < 1H to 1V	4,000 lb/ac	4,500 kg/ha
> 1H to 1V	4,500 lb/ac	5,100 kg/ha
Below ECB or TRM	1,500 lb/ac	1,700 kg/ha
As infill for TRM*	3,500 lb/ac	3,900 kg/ha

*Use only approved and tested Futerra® Turf Reinforcement Mats (TRMs) to create the GreenArmor™ System

For additional details including mixing ratios/loading rates for specific machine sizes and visual keys for proper application, please consult Profile® Application Guide for HP-FGM™ and ET-FGM™.

3.05 CLEANING AND PROTECTION

- A. Always flush residual slurry from hydraulic seeding/mulching equipment immediately following each application, at the end of each work period or when equipment will be left unattended. Compounds containing residual Urea, Nitrogen, Phosphorus, Potassium and other substances may form and can be hazardous to human health and equipment.
- B. Clean spills promptly. Advise owner of methods for protection of treated areas. Do not allow treated areas to be trafficked or subjected to grazing.

3.06 INSPECTION AND MAINTENANCE

- A. All inspections and maintenance recommendations shall be conducted by qualified professionals consistent with the owner, engineer/specifier and regulatory entity(ies) expectations.
- B. Initial inspections shall insure installations are in accordance with the project plans and specifications with material quantities and activities fully documented. Refer to Section 32 92 00 – Turf and Grasses for any additional details.
- C. Subsequent inspections shall be conducted at pre-determined time intervals and corrective maintenance activities directed after each significant precipitation or other potentially damaging weather or site event.

© 2021 PROFILE Products LLC. All Rights Reserved. A copyright license to reproduce this specification is hereby granted to non-manufacturing landscape architects, specification writers and designers.

Revision Date: 08/2021