

ALABAMA DEPARTMENT OF TRANSPORTATION

DATE: July 13, 2012

Special Provision No. 12-0355

EFFECTIVE DATE: November 1, 2012

SUBJECT: Mineral Filler, Hydrated Lime, Calcium Chloride, Brick, and Blocks.

Alabama Standard Specifications, 2012 Edition, SECTION 805 shall be replaced by the following:

SECTION 805 MINERAL FILLER, HYDRATED LIME, CALCIUM CHLORIDE, BRICK, AND BLOCKS

805.01 Mineral Filler, Hydrated Lime, Calcium Chloride, Brick, and Blocks.

These minerals shall meet the following requirements:

Mineral Filler	AASHTO M 17
Hydrated Lime	ASTM C 207, Type N.
Calcium Chloride	AASHTO M 144, Type S or L
Sewer Brick	AASHTO M 91, Grade S.M. or M.M.
Building Brick (Clay or Shale)	ASTM C 62, Grade S.W. or M.W.
Concrete Brick (Manholes, etc)	ASTM C 55, Type 11, Grade S
Concrete Brick (Buildings)	ASTM C 55, Type 1, Grade N-I or N-II
Concrete Block (Hollow Load Bearing)	ASTM C 90, Grade N, Type I or II

805.02 Mineral Filler for Hot Mix Asphalt.

These minerals shall consist of finely divided mineral matter such as crusher fines, rock dust, slag dust, hydrated lime, hydraulic cement, Portland cement, loess or Class "F" fly ash meeting the requirements of AASHTO M 17. Any lime based product shall meet the requirements of AASHTO M 303.