

ALABAMA DEPARTMENT OF TRANSPORTATION

DATE: January 7, 2015

Special Provision No. 12-1315

EFFECTIVE DATE: April 1, 2015

SUBJECT: Bituminous Surface Treatments.

Alabama Standard Specifications, 2012 Edition, SECTION 401 shall be revised as follows:

SECTION 401 BITUMINOUS SURFACE TREATMENTS

401.02 Materials.

(a) BITUMINOUS MATERIALS, SECTION 804.

1. PRIME:

Item 1 of Subarticle 401.02(a) shall be replaced with the following:

1. PRIME:

Emulsified Asphalt	AE-P, CRS-1h, CMS-1hp, or NTSS-1HM
Cutback Asphalt	MC 30 or MC 70 for tight bases; MC 250, RC 70 or RC 250 for open bases.
Emulsified Petroleum Resin	EPR *

* This material shall not be used as a prime on processed reef shell base courses, crushed aggregate base courses, or rubblized concrete. This material shall not be left exposed for more than four days before placing a base layer of asphalt over it. This material shall also be supplied from the producer in the form in which it shall be placed. Material in a concentrated form that requires dilution after delivery will not be allowed.