

**Bituminous Surface Treatments and Latex Modified
Bituminous Surface Treatment**

Type of Construction	Material	Test	Frequency of Acceptance Samples and Tests for Job Control	Construction Stages for Obtaining Sample or Test	Sample Size	Procedures		Remarks
						Sampling Method	Test Methods	
Bituminous Surface Treatments and Polymer Modified Bituminous Surface Treatment	Liquid Bituminous Material	Analysis	See ALDOT-243 Sample tank when plant has been idle for extended period of time or has used different paving grades of asphalt material or has not received BMT-146 for shipments	Before incorporation in work	1 qt (1 L) for Performance Graded Asphalt Binder (PGAB). 1 gal. (4 L) for emulsified asphalts	AASHTO T-40		Ship to Central Laboratory. Use metal cans for Liquid Binder. Use plastic containers for emulsified asphalts. Sample information card Form BMT-1. If contamination is suspected, sample as required by Engineer
		Application Rate	See Construction Manual for frequencies, methods and, reports					
	Polymer Modified Liquid Bituminous Material	Analysis	See ALDOT-243 Sample tank when plant has been idle for extended period of time or has used different paving grades of asphalt material or has not received BMT-146 for shipments	Before incorporation				
	Aggregate	Gradation	Pretested. See ALDOT-249	Before incorporation in work.	AASHTO T-27	AASHTO-T-2	AASHTO T-27, T-19	Report on Form BMT-91
		Unit Weight		See ALDOT-195			ALDOT-253	