

**Bituminous Surface Treatments and Latex Modified
 Bituminous Surface Treatment**

Type of Construction	Material	Test	Frequency of Acceptance Samples and Tests for Job Control	Construction Stages for Obtaining Sample or Test	Sample Size	Procedures		Remarks
						Sampling Method	Test Methods	
Bituminous Surface Treatments and Polymer Modified Bituminous Surface Treatment	Liquid Bituminous Material	Analysis	See ALDOT-243. For projects including 2,000 square yards or more sample tank once per material per job. For all projects sample the tank when plant has been idle for an extended period of time, or has used different paving grades of asphalt material, or has not received BMT-146 for shipments.	Before incorporation in work	1 qt (1 L) for Performance Graded Asphalt Binder (PGAB). 1 gal. (4 L) for emulsified asphalts	AASHTO T-40		Ship to Central Laboratory. Use metal cans for Liquid Binder. Use plastic containers for emulsified asphalts. Sample information card Form BMT-1. If contamination is suspected, sample as required by Engineer
		Application Rate	See Construction Manual for frequencies, methods and, reports					

**Bituminous Surface Treatments and Latex Modified
 Bituminous Surface Treatment**

	Polymer Modified Liquid Bituminous Material	Analysis	See ALDOT-243. For projects larger than 2,000 square yards Sample tank once per material per job. for all projects sample the tank when and when plant has been idle for an extended period of time, or has used different paving grades of asphalt material, or has not received BMT-146 for shipments	Before incorporation				
	Aggregate	Gradation Unit Weight	Pretested. See ALDOT-249	Before incorporation in work. See ALDOT-195	AASHTO T-27	AASHTO-T-2	AASHTO T-27, T-19 ALDOT-253	Report on Form BMT-91